

SM3-23 Overexpanded Polyolefin 3:1 Shrink Ratio

Technical Specifications:

SAE AS23053/5, Class 1
(with exception to dimensions
and longitudinal change)
UL 224 125°C, 600v
UL/CSA VW-1, 125°C, 600 volts
RoHS/RoHS 2 Compliant

Electrical

Chemical

Print Adherence

Property	Test Method	Requirement
Tensile strength (psi)	ASTM D 638	1500 min.
Elongation (%)	ASTM D 638	200 min.
Specific gravity	ASTM D 792	1.35 max.
Low temperature flex (-55°C)	AMS-DTL-23053	no cracking
Heat shock (250°C, 4 hrs.)	AMS-DTL-23053	no cracking
Heat resistance (175°C, 168 hrs)		
Secant modulus (psi)	ASTM D 882	2.5 x 10 ⁴ max.
Longitudnal change (%)	AMS-DTL-23053	+5, -15
Dielectric strength (volts/mil)	ASTM D 876	500 min.
Volume resistivity (ohm-cm)	ASTM D 876	1.0 x 10 ¹⁴ min.
Corrosion (175°C, 16 hrs.)	AMS-DTL-23053	no corrosion
Water absorption (%)	ASTM D 570	0.5 max.
Fluid resistance (23°C, 24 hrs.)		
Tensile strength (psi)	AMS-DTL-23053	1000 min.
Flammability	UL 224 VW-1	Pass
Shrink temperature, nominal		90°C
Abrasion (eraser method)	SAE AS5942	20 rubs
Fluid Resistance:	MIL-STD-202G, Method 215	
Isopropyl Alcohol/Mineral Spirits Blend		10 rubs (x3)
Terpene Defluxer		10 rubs (x3)
H ₂ O/PGME/Monoethanolamine		10 rubs (x3)
UV Resistance: 720 hrs. xenon arc lamp exposure		marks legible

We can help: 800 758 3515

customerservice@seipusa.com

www.seipusa.com

Product insight

Rev. A, May 2022

Standard Sizes:

Please see table to the right for standard sizes. Custom sizes and colors are available with minimum order quantities.

Standard Colors:

White, black, yellow.

Dimensional Information:

Please refer to diagram to the right for dimensions.

Standard Package:

Continuous, spooled. Feet.

How to order:


Example: SM3-23, 1/4", White

SM3-23

Page 3 of 3

Overexpanded Polyolefin 3:1 Shrink Ratio

Size	ID Min (as supp.)		ID Max (after recov.)		Wall Thickness Nom (after recov.)		Packaging (per spool)
	inch	mm	inch	mm	inch	mm	
1/16	.063	1.6	.021	0.5	.020	0.50	1,000
1/8	0.125	3.2	.043	1.1	.024	0.60	500
3/16	.188	4.8	.063	1.6	.026	0.65	200
1/4	.250	6.4	.083	2.1	.028	0.70	200
3/8	.375	9.5	.122	3.1	.031	0.80	200
1/2	.500	12.7	.165	4.2	.033	0.85	200
3/4	.750	19.1	.248	6.3	.039	1.00	200
1	1.00	25.4	.327	8.3	.048	1.20	200
1.5	1.50	38.1	.500	12.7	.050	1.30	200



Type of material	Size	Color	Packaging
SM3-23	1/4	White	Spool

We can help: 800 758 3515

customerservice@seipusa.com

www.seipusa.com